

DALLAS LABORATORIES, INC.

Consultants and Technologists
Chemical and Petroleum Chemists

P.O. BOX 152837, DALLAS, TEXAS 75315
1323 WALL ST, DALLAS, TEXAS 75215
PHONE 214/565-0593
FAX 214/565-1094

MEMBERS
AMERICAN CHEMICAL SOCIETY
ASTM INTERNATIONAL
AMERICAN SOCIETY OF MATERIALS

MEMBERS
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: Omniroc, Inc.
Advanced Heat Exchange, Inc.
2995 LBJ Frwy., Suite 224
Dallas, TX 75234

Date: September 24, 2009

Attn: Chuck Armstrong

Report No: 41694-J

REPORT

Lab Sample No.

41694 Cement Board (1/2")

PROCEDURE / INTRODUCTION

Sample was tested for Flame Spread. The test is conducted in accordance with the procedure outlined in ASTM E84-08a, *Standard Test Method for Surface Burning Characteristics of Building Materials* (NFPA 255, ANSI/UL 723 and UBC 8-1).

Test specimens are conditioned in an atmosphere maintained between 68 and 78 °F and 45 to 55% relative humidity. Immediately prior to the test, the specimen is mounted in the furnace with the side to be tested facing the test flame. Cement board is placed on the unexposed side of the specimen to protect the furnace lid assembly. The test is conducted with the material in the ceiling position.

The flame front position and light obscuration are recorded throughout the 10-minute test and used to calculate the Flame Spread and Smoke Developed indices. The temperature at 23 ft is also recorded. The Flame Spread and Smoke Developed indices reported herein are relative to the results obtained for mineral fiber-reinforced cement board and select grade red oak.

The results apply specifically to the specimens tested, in the manner tested, and not to the entire production of these or similar materials, nor the performance when used in combination with other materials. For reference purposes, the IBC/NFPA classification criteria are listed below:

Classification	Flame Spread Index (FSI)	Smoke Developed Index (SDI)
A	0 - 25	0 - 450
B	26 - 75	0 - 450
C	76 - 200	0 - 450

RESULTS

Description

Material:
Thickness:

Sample

Cement Board
½" (Nominal)

Calibration/Set-Up

Calibration Media:
Flame Spread and Smoke Basis
Moisture (Red Oak):
Leakage Test:

Red Oak/Cement Board
100 / 0
6-8%
Acceptable

Test/Data

Raw Flame Spread Factor: 0.0
Raw Smoke Generation Factor: 3.2

Observations During Test

Ignition Time: 0.0 Seconds
Time to Max Temperature 9.75 Minutes
Max Temperature: 536°F
Sagging: None
Dripping: None
Shrinkage: None
After Flame:
 Top: None
 Bottom: None
Fallout: None
Delamination: None
Flaming on Floor: None


Final Test Results

Flame Spread Index (FSI) 0
Smoke Developed Index (SDI) 5

CONCLUSION

Sample meets **Class A** for Flame Spread of 25 or less. Sample also has a very low smoke development.

DALLAS LABORATORIES, INC.


Kévan W. Jones, Vice President

Analyst: KJ, TL
KWJ: js